



PRO GOLD TRACK MIX

1. The Track Mix shall consist of crushed-screened 3/16 inch to 3/8 inch minus decomposed granite fines as produced by Gail Materials
2. For installation of new tracks place Pro Gold Track Mix to a minimum depth of 4 inches compacted.
3. Spread the material over the entire surface area and apply water so that the entire depth of material is moist. Level to desired grade. After a period of +/- 6 hours compact the final lift with a minimum 2000 lb. static drum roller. Allow for the material to thoroughly dry and cure before activity on the new track surface. It should be noted that for a level surface it is recommended to grade the area with a laser level or similar.

AGGREGATE GRADATION	
Sieve Size	Percent Passing
3/8"	95 - 100
3/16"	95 - 100
No. 4	90 - 100
No. 30	25 - 55
No. 200	5 - 15

- I. Sand Equivalent – minimum 30
- II. Color – Gold to Reddish Gold

Supplier – Gail Materials (951) 667-6106, www.gailmaterials.net

GAIL MATERIALS

10060 Dawson Canyon Road, Corona, CA 92883
(951) 667-6106 • Fax (951) 667-6102

www.gailmaterials.net