



### PRO GOLD TRACK MIX W/ CINDER SAND

1. The Track Mix shall consist of 70-80% crushed-screened 3/16 inch minus decomposed granite fines and 20-30% Cinder Sand as produced by Gail Materials
2. For installation of new tracks place Running Track Mix w/ Cinder Sand to a minimum depth of 4 inches compacted.
3. For each 2 inch lift evenly spread the material over the entire surface area and apply water so that the entire depth of material is moist. Level to desired grade. After a period of +/- 6 hours compact the final lift with a minimum 2000 lb. static drum roller. Allow for the material to thoroughly dry and cure before activity on the new track surface. It should be noted that for a level surface it is recommended to grade the area with a laser level or similar.

AGGREGATE GRADATION	
Sieve Size	Percent Passing
3/16"	95 - 100
No. 4	90 - 100
No. 30	25 - 60
No. 200	5 - 20

- I. Sand Equivalent – minimum 30
4. Supplier – Gail Materials (951) 667-6106, [www.gailmaterials.net](http://www.gailmaterials.net)